



SCM[®]
SuperCorrMedium



ESPECIFICACIONES TÉCNICAS DE PAPEL Super Corrugated Medium

Peso Básico	Estándar		146	160	195
Tappi T410	Mínimo		142	156	190
(g/m ²)	Máximo		150	165	200
			146	160	195
Humedad	Estándar		7.5	7.5	7.5
Tappi T412	Mínimo		6.5	6.5	6.5
(%)	Máximo		9.0	9.0	9.0
			146	160	195
Calibre	Estándar		0.26	0.28	0.34
Tappi T411	Mínimo		0.20	0.22	0.27
(mm)	Máximo		0.31	0.34	0.41
			146	160	195
SCT CD	Estándar	(kN/m)	2.60	3.00	3.40
Tappi T826	Mínimo	(kN/m)	2.40	2.80	3.20
	Estándar	(lbf/in)	14.8	17.1	19.4
	Mínimo	(lbf/in)	13.7	16.0	18.3
			146	160	195
Concora (CMT)	Estándar	(kg)	32	36	39
Tappi T809	Mínimo	(kg)	30	34	36
	Estándar	(N)	314	353	382
	Mínimo	(N)	294	333	353
			146	160	195
Cobb	Máximo		50	45	45
Tappi T441	Mínimo		30	25	25
(g/m ²)	Tiempo ensayo		1	2	
	(min)				



The mark of
responsible forestry



www.papeleranacional.com

Guayaquil Ecuador