



ESPECIFICACIONES TÉCNICAS DE PAPEL T. LINER PANASA

Peso Básico	Standard	150	170	205	230	270
Tappi T410	Mínimo	146	165	200	225	264
(g/m ²)	Máximo	154	175	210	235	276

		150	170	205	230	270
Humedad	Estándar	7.5	7.5	7.5	7.5	7.5
Tappi T412	Mínimo	6.5	6.5	6.5	6.5	6.5
(%)	Máximo	9.0	9.0	9.0	9.0	9.0

		150	170	205	230	270
Calibre						
Tappi T411	Mínimo	0.21	0.25	0.27	0.31	0.37
(mm)	Máximo	0.32	0.36	0.39	0.44	0.50

		150	170	205	230	270
SCT CD	Estándar (kN/m)	2.63	2.98	3.59	4.16	4.73
Tappi T826	*Mínimo (kN/m)	2.42	2.74	3.30	3.70	4.35
	Estándar (lbf/in)	15.0	17.0	20.5	23.8	27.0
	Mínimo (lbf/in)	13.8	15.6	18.8	21.1	24.8

* Mínimo no aplica para pads.

		150	170	205	230*	270
Mullen	Estándar (psi)	65	74	80	90	95
Tappi T807	Mínimo (psi)	60	68	74	80	90
	Estándar (kPa)	448	510	552	621	655
	Mínimo (kPa)	414	469	510	552	621

* mínimo pads: 86 psi

		150	170	205	230	270
Cobb(120 seg.)	Máximo	45	45	45	45	45
Tappi T441	Mínimo	25	25	25	25	25
(g/m ²)						

* pads: min 20 max 40